

Technical Information

Wire Enamels I Mitshock G



MITSHOCK G

Type

MITSHOCK G is wire enamel based on modified Polyester having excellent shine with attractive golden colour & suitable for thicker to medium wires.

Specifications

Properties	Test Method	Unit	Specification
Specific Gravity at 25°C	ASTM D 891		1.10 + / - 0.02
Viscosity			
By Ford Cup B4 at 30°C	IS 3944	Seconds	90 to 100
By Brookfield at 25°C	ASTM D - 2196	M pas	450 - 500
Solid Content (1gm / 2hrs / 180°C)	ASTM D - 1353	Percentage	35 ± 1
Flash Point	ASTM D - 93	Degree in Celsius	45°C

Recommended Thinner - for thinning the enamel a special THINNER is recommended.

Application - By Dies or Felt Pads.

Packing - 210 kgs / 25 kgs in MS New barrels / drums.

Representative properties of enameled wire as per IEC - 60851 part 1 to 6 & 60317 - 34

Properties	Unit	Specification
Conductor Diameter	Millimeter	1.00
Increase in Diameter	Millimeter	0.075
Colour		Golden
Mechanical Tests		
Jerk Test		OK
Peel Test	Revolution	N.A.
Elongation	Percentage	38
Flexibility		1xd - OK
Resistance to Abrasion	Unidirectional - Newton	12.48
Thermal Tests		
Heat Shock at 180°C		5d - OK
Cut Through	Degree in Celsius	250 - OK
Thermal Class	Degree in Celsius	130
Electrical Tests		
Breakdown Voltage	Kilovolt (KV)	9.5
Tandelta Bending Point	Degree in Celsius	103
Chemical Test		
Solvent Resistance	Pencil Hardness (H)	3H

Note - All technical properties are for guidance only. Our data reflect the latest of our knowledge and are based on the characteristics established in the laboratory and on practice experience. No warranties of any kind, either expressed or implied, are made regarding the products here described.